



**Era Polymers Pty. Ltd.**  
25-27 Green Street, Banksmeadow  
Sydney, NSW 2019  
AUSTRALIA  
www.erapol.com.au

## Erapol RN90A

HIGH PERFORMANCE POLYESTER  
POLYURETHANE

### TECHNICAL DATASHEET

**Erapol RN90A** is an isocyanate-terminated polyester based urethane prepolymer. It is formulated for use with MOCA curative. It features longer gel time and lower viscosity than Erapol RN3039 for easier processing.

**Erapol RN90A** elastomers provide properties generally not available with rubbers, plastics or metals. They show improved solvent and oil resistance and better thermal stability than most general-purpose rubbers and plastics. Other outstanding properties include high abrasion and tear resistance, excellent load-bearing capacity, toughness and resiliency.

#### Product Specification

% NCO	4.55 ± 0.15
Viscosity at 80°C (cps)	1200 - 1800
Colour	Clear, light amber

#### Mixing and Curing Conditions

		RN90A / MOCA	RN90A / Ethacure 300	RN90A / Eracure 110
Erapol RN90A	(pph)	100	100	100
MOCA Level	(pph)	13.7	-	-
Ethacure 300 level	(pph)	-	11.0	-
Eracure 110 level	(pph)	-	-	11.8
Recommended % Theory		95	95	95
Erapol Temperature	(°C)	80	65	65
Curative Temperature	(°C)	110 - 120	25 - 30	25 - 30
Pot Life*	(mins)	4	4	4
Demould Time** at 100°C	(hrs)	1	1	1
Post Cure Time at 100°C	(hrs)	16	16	16

\* Pot life based on a 200g sample, prepolymer at 80°C, MOCA at 100°C

\*\* Demould time based on a 200g rectangular slab. Demould time will depend on the size and shape of the cast part.



This information is of general nature and is supplied without recommendation of guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Era Polymers cannot accept liability for loss or damage through use. Whilst these technical details are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are supplied. Users must, by comprehensive testing, evaluate this product in their own application.

## Physical Properties

Properties presented below are to be used as a guide and not intended for specification purposes.

		RN90A/MOCA	RN90A/E300	RN90A/E110	TEST METHOD
<b>Hardness</b>	(Shore A)	90 ± 3	85 ± 3	85 ± 3	AS1683.15
<b>Tensile Strength</b>	MPa (psi)	53.0 (7687)	45.0 (6527)	45.0 (6527)	AS1683.11
<b>100% Modulus</b>	MPa (psi)	5.2 (754)	-	-	AS1683.11
<b>200% Modulus</b>	MPa (psi)	10.3 (1494)	-	-	AS1683.11
<b>Angle Tear Strength, Die C</b>	(kN/m)	100	100	90	AS1683.12
<b>Trouser Tear Strength</b>	(kN/m)	45	45	40	AS1683.12
<b>Elongation</b>	(%)	650	690	700	AS1683.11
<b>DIN Resilience</b>	(%)	40	40	40	DIN 53512
<b>DIN Abrasion Resistance 10N</b>	(mm <sup>3</sup> )	60	60	40	AS1683.21
<b>DIN Abrasion Resistance 5N</b>	(mm <sup>3</sup> )	30	30	20	AS1683.21
<b>Compression Set / 22 hr at 70°C</b>	(%)	30	-	-	AS1683.13
<b>Cured Specific Gravity</b>	(g/cm <sup>3</sup> )	1.26	1.25	1.25	AS1683.4

## Processing Procedure

1. Heat pre-weighed amounts of **Erapol RN90A** to 80-100°C and degas at -95kpa of vacuum for at least 5 minutes or until excessive bubbling stops. Containers should be unlined metal, plastic or glass and should be large enough to allow for foaming during degassing.
2. MOCA must be melted at 120°C prior to mixing. After adding MOCA, mix thoroughly and degas at -95kpa for 1 to 2 minutes.
3. Pour mixed system into moulds, preheated to 100°C, that have been coated with **Salease** mould release or equivalent.
4. Cure in accordance with above recommendations.

## Adhesion

Adhesion of Erapol based elastomers to various substrates is at best marginal if a primer is not used. Please consult Era Polymers for specific recommendations to improve adhesion.

## Handling Precautions

Consult the product's material safety data sheet (MSDS) for specific hazard and handling information before use.

**Erapol RN90A** contains small amounts of free TDI. Therefore the product should be used in well-ventilated areas. Avoid breathing in vapours and protect skin and eyes from contact.

In case of skin contact, immediately remove excess, wash with soap and water. For eye contact, immediately flush with water for at least 15 minutes.

If nose, throat or lungs become irritated from breathing in vapours, remove exposed person to fresh air. Call a physician.